(A)] at least one homogeneously branched linear ethylene/α-olefin interpolymer having:

  (i) a density from about 0.89 grams/cubic centimeter (g/cm^3) to about [0.92] 0.935 g/cm^3,

  (ii) a molecular weight distribution (M_w/M_n) from about 1.8 to about 2.8,

  (iii) a melt index (I_2) from about 0.001 grams/10 minutes (g/10 min) to about 10 g/10 min,

  (iv) no [linear polymer] high density fraction, [and]

  (v) a single melting peak as measured using differential scanning calorimetry[,], and

  (vi) a slope of strain hardening coefficient greater than or equal to 1.3; and

(B) from about 5 percent (by weight of the total composition) to about 90 percent (by weight of the total composition) of at least one heterogeneously branched ethylene polymer having a density from about 0.93 g/cm^3 to about 0.965 g/cm^3.

10. (Amended) The film of claim 9 wherein the homogeneously branched linear ethylene [polymer] interpolymer has a slope of strain hardening coefficient greater than or equal to [about 1.3] 1.5.

---

24. (Amended) [In a] An ethylene polymer composition comprising [at least one homogeneously branched ethylene/α-olefin interpolymer and at least one heterogeneously branched ethylene/α-olefin interpolymer, the improvement comprising incorporating into the composition] (A) from about 10 percent (by weight of the total composition) to about 95 percent (by weight of the total composition) of at least one homogeneously branched linear ethylene/α-olefin interpolymer having:

  (i) a density from about 0.89 grams/cubic centimeter (g/cm^3) to about [0.92] 0.935 g/cm^3,

  (ii) a molecular weight distribution (M_w/M_n) from about 1.8 to about 2.8,

  (iii) a melt index (I_2) from about 0.001 grams/10 minutes (g/10 min) to about 10 g/10 min,

  (iv) no [linear polymer] high density fraction, [and]

  (v) a single melting peak as measured using differential scanning calorimetry, and

  (vi) a slope of strain hardening coefficient greater than or equal to 1.3; and

(B)   from about 5 percent (by weight of the total composition) to about 90 percent (by weight of the total composition) of at least one heterogeneously branched ethylene polymer having a density from about 0.93 g/cm³ to about 0.965 g/cm³.

25.   (Amended)   The [improvement] composition of claim 24 wherein the homogeneously branched linear ethylene/α-olefin interpolymer has a slope of strain hardening coefficient greater than or equal to [about 1.3] 1.5.

26.   (Amended)   The [improvement] composition of claim 24 wherein the homogeneously branched linear ethylene/α-olefin interpolymer is an interpolymer of ethylene with at least one C_3-C_{20} α-olefin.

27.   (Amended)   The [improvement] composition of claim 24 wherein the homogeneously branched linear ethylene/α-olefin interpolymer is a copolymer of ethylene and a C_3-C_{20} α-olefin.

28.   (Amended)   The [improvement] composition of claim 27 wherein the homogeneously branched linear ethylene/α-olefin interpolymer is a copolymer of ethylene and 1-octene.

29.   (Amended)   The [improvement] composition of claim 24 wherein the heterogeneously branched ethylene polymer is a copolymer of ethylene and a C_3-C_{20} α-olefin.

30.   (Amended)   The [improvement] composition of claim 29 wherein the heterogeneously branched ethylene polymer is a copolymer of ethylene and 1-octene.

Please add the following new claim:

--31.   The film of Claim 9 or the composition of Claim 24, wherein the density of the at least one homogeneously branched linear ethylene/α-olefin interpolymer is in the range from about 0.905 g/cm³ to about 0.925 g/cm³ and the I_2 melt index is in the range of from about 0.001 g/10 minutes to less than about 1 g/10 minutes.--